

Kerax Ltd - Technical Data Sheet

Date Prepared: 06 Aug 2008

Date Revised: 01MAY20

Version: 3.0

TDS - Kerawax 2245

Information

Product Description

Kerawax 2245 is a fully refined low melt point paraffin wax.

Physical Properties

Test	Method	Specification	Typical	
Congealing Point	ASTM D938	40 – 43.5	42°C	
Viscosity @100°C	D445	2 – 3	2.5cSt	
Penetration @25°C	ASTM D1321	46 – 60	50 dmm	
Colour, Saybolt	ASTM D156	25 Min	30	
Odour	In House	Pass	Pass	

Statement

- Formulated from materials whose refining history is fully traceable.
- Does not contain or come into contact with any animal or GMO products at any stage of its manufacture.
- Does not contain residual solvents as per guidelines CPMP/ICH283/95.
- Has not been tested on animals by ourselves or on our behalf.

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users must make their own tests to determine the suitability of these products for their own particular purposes. The company makes no warranty of any kind, expressed or implied, including those of merchantability or fitness for a particular purpose, other than that the material conforms to its applicable current Standard Specifications.