

Date Prepared: 06 Mar 2013 Date Revised: 09 Sep 2015 Version: 3.0

TDS – Techniwax 9300

Information

Product Description

Techniwax 9300 is a fully refined microcrystalline wax.

Physical Properties

Test	Method	Typical
Congealing Point °C	ASTM D 938	76
Viscosity @ 100°C	ASTM D 445	19 cSt
Penetration@ 25°C	ASTM D 1321	61 dmm
Penetration@ 43.4°C	ASTM D 1321	163 dmm
Colour	ASTM D 156	22

Statement

- Formulated from materials whose refining history is fully traceable.
- Does not contain or come into contact with any animal or GMO products at any stage of its manufacture
- Does not contain residual solvents as per guidelines CPMP/ICH283/95.
- Has not been tested on animals by ourselves or on our behalf.

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users must make their own tests to determine the suitability of these products for their own particular purposes. The company makes no warranty of any kind, expressed or implied, including those of merchantability or fitness for a particular purpose, other than that the material conforms to its applicable current Standard Specifications.